



Information analysis:

Bitumen road no TU Mark 70/100 СТБ EN12591-2010

№ паспорта: 1853

№	Лаб	Показатель	Норма	FACT
1	М	Penetration at 25°C, 0,1 мм	range 70-100	90
2	М	Softening poin	range 43,0 - 51,0	47,4
3	М	Residual penetration,%	not less than 46	95
4	М	Increased softening temperature, ° C	Not more than 9,0	5
5	М	Change of mass%	Not more than 0,80	0,03
6	М	Temper flare in restaurants. TIG, ° C	not less than 46	304
7	М	Growing up in Tol. chloroform or	not less 99,00	99,95
8	М	penetration index	range -1,5 - 0,7	-0,3
9	М	Viscosity din. at 60 ° C, Pa * s	Not less 90	223
10	М	brittleness temperature, ° C	Not higher -10	-17
11	М	Kinem. vyazkost' pri 135°S, mm2/s	Not lesse 230	505